



National Fire Equipment Ltd.

MYTI-FLO®

A circular woven, seamless, all synthetic hose
featuring “lowest friction loss lining.”

Applications

- Forestry mop-up and sprinkler hose
- Cottage and forestry home values protection hose
- Decontamination and wash down hose
- Industrial applications hose
- Marine fire hose and RV potable water (when specified)

Diameters

- 5/8in/16mm
- 3/4in/19mm



Features and Benefits

- Seamless, light weight, and multipurpose
- Unique Mertex® lining
- Premium all synthetic single jacket
- Available with Permatak HP™ treatment against abrasion, moisture pick up and mildew
- Resistant to most chemicals, petrol products, ozone and U.V. exposure, hydrolysis, rot and mildew
- Remains flexible to -65° F (-55° C)
- Meets or exceeds all performance requirements of NFPA 1961, Underwriters Laboratories and Factory Mutual
- Available with both GHT and patented Baby Merlug® 3/4"/19mm QC couplings

Standard White/Yellow Permatak HP available

Trade Size		Bowl Size		Weight Un-coupled 100'(30.5M)		Coil Diameter 100'(30.5M)		Service Pressure		Proof Pressure		Burst Pressure	
In.	mm	In.	mm	LBS	Kg	In.	Cm.	PSI	kPa	PSI	kPa	PSI	kPa
5/8	16	N/A	N/A	1.5	0.7	8.0	20.3	250	1725	500	3450	750	5175
3/4	19	N/A	N/A	1.7	0.8	8.0	20.3	250	1725	500	3450	750	5175



National Fire
Equipment Ltd.

TORONTO: (905) 761-6355
Toll Free: (800) 267-8508

OTTAWA: (613) 723-6071

VANCOUVER: (604) 420-1131
Toll Free: (800)-667-2138

BURNABY: (604)-299-4498

EDMONTON: (780) 455-3870
Toll Free: (888)-891-1008

CALGARY: (403) 236-5661

MONCTON: (506) 859-7277
Toll Free: (877) 816-3473

MISSISSAUGA: (905) 565-1385

www.nationalfire.com



National Fire Equipment Ltd.

MYTI-FLO®

THE HOSE SHALL BE SINGLE JACKET WITH A SERVICE TEST PRESSURE OF 250 PSI / 1725 KPA.

JACKET

The hose jacket shall be made with high tenacity filament polyester yarn in both the warp and weft directions, to provide maximum strength to weight ratio and shall have a minimum filler (weft) yarns of 12.3 per inch (484 per Meter).

When requested the jacket shall be impregnated in one of the standard NFPA colors with high performance polymeric dispersion.

LINING

The lining (waterway) must be made from polyurethane and must be applied using a fused process that welds the polyurethane directly to the textile while the hose is being woven, without the use of adhesives or hot melt. The fused lining process must create a virtually inseparable unit without the use of adhesives, yielding an extremely low friction (pressure) loss by filling in the corrugations of the weave, creating an ultra thin and smooth waterway. Fire hose made using adhesives of any type do not meet this specification. The lining shall be approved for use with potable water.

ADHESION

The adhesion shall be such that the rate of separation of a 1 1/2" / 38mm strip of polyurethane, transversely cut, shall not be greater than 1/4" / 6mm per minute under a weight of 12 lbs / 5.5 kg.

SERVICE, TEST, BURST PRESSURES

Minimum service, test and burst pressures shall be as detailed in the specification table on the previous page.

KINK TEST

A full length will withstand a hydrostatic pressure of 600 psi / 4140 kPa while kinked.

WEIGHT

Each length of fire hose shall not weigh more than indicated in the specification table.

COUPLING SPECIFICATIONS

The hose shall be available with both GHT and 3/4" 19mm quarter-turn threadless (QC) couplings.

MANUFACTURE

Both hose and couplings must be manufactured in North America and be NAFTA compliant.



National Fire
Equipment Ltd.

TORONTO: (905) 761-6355
Toll Free: (800) 267-8508

OTTAWA: (613) 723-6071

VANCOUVER: (604) 420-1131
Toll Free: (800)-667-2138

BURNABY: (604)-299-4498

EDMONTON: (780) 455-3870
Toll Free: (888)-891-1008

CALGARY: (403) 236-5661

MONCTON: (506) 859-7277
Toll Free: (877) 816-3473

MISSISSAUGA: (905) 565-1385

www.nationalfire.com